

PRODUCT DESCRIPTION

SOL XVI it is a standard letdown varnish.

CHARACTERISTICS

Based in modified phenolic resins, vegetable oil and mineral oil.

Solid content: +/- 55%.

Good press stability.

Good lithographic properties.

High gloss.

PRODUCT SPECIFICATIONS¹

	Product Specification	Typical Properties	Units
Viscosity (Rheometer, 23°C, 25 s ⁻¹)	250 – 300	275	Pa.s
Cloud Point (10% in T.O. 6/9 AF New)	120 – 150	140	°C
Tack (Lithotack, 0.4 gr, 32.2°C, 400rpm, 60'')	80 – 120	100	-----

APPLICATIONS

Sheetfed offset inks.

FORM OF SUPPLY

Open lid drums (190 kg);

Road tanks.

SHELF LIVE

Up to six months under normal storage conditions.

¹Analytical Methods are available on request

The information in this Technical Data Sheet is, to the best of our knowledge, true and accurate, but since the conditions of use are beyond our control, no warranty is given or to be implied in respect of such information. We are, at all times, willing to study customer's specific outlets involving our products in order to enable their most effective use.