

PRODUCT DESCRIPTION

SOL XVIII is a standard sheetfed varnish.

CHARACTERISTICS

Based in phenol free resin and vegetable oils.

Solid content: +/- 95%.

Good lithographic properties.

PRODUCT SPECIFICATIONS¹

	Product Specification	Typical Properties	Units
Viscosity (Rheometer, 23°C, 25 s ⁻¹)	200 - 280	240	Pa.s
Cloud Point (10% in T.O. 6/9 Af New)	90 - 140	120	°C
Tack (Lithotack, 0.4 gr, 32.2°C, 400rpm, 60'')	100 - 150	120	-----

APPLICATIONS

Sheet-fed offset inks.

FORM OF SUPPLY

Open lid metallic drums (190 Kg). Road Tanks.

SHELF LIVE

Up to six months under normal storage conditions.

¹Analytical Methods are available on request

The information in this Technical Data Sheet is, to the best of our knowledge, true and accurate, but since the conditions of use are beyond our control, no warranty is given or to be implied in respect of such information. We are, at all times, willing to study customer's specific outlets involving our products in order to enable their most effective use.